Technical data sheet



Merbenit DB50

Merbenit DB50 is an elastic adhesive for large area bonding in the range of boat and ship building. Thanks to SMP base suitable for many timber and plastics with excellent processing. Merbenit DB50 is in particular resistant to environmental influences. Meets the requirements of the International Maritime Organisation IMO.

Product advantages

- Simple processing
- Long processing time
- Good ridge
- Dimensionally stable, no flowing on inclined surfaces
- Impurities can be removed easily
- High elasticity, good mechanical strength
- Free of solvents, isocyanates and silicones
- Odourless
- Impact and vibration resistant (shock absorbing)
- Very wide adhesion range

Technical data

| Chemical base | Silane modified polymer |
|---|------------------------------------|
| Mechanism of curing | 1 comp. moisture curing |
| Consistency | good ridge, efficiently trowelable |
| Tooling time | max. 60 min. |
| Curing rate after 24h | ≥ 2.0 mm |
| Curing rate after 48h | ≥ 3.0 mm |
| Shore-A-hardness, DIN ISO 7619-1 | 38 |
| Tensile strength DIN 53504 S2* | ca. 1.6 N/mm² |
| Modulus elongation at 100%, DIN 53504 S2 * | ca. 1.0 N/mm² |
| Elongation at break, DIN 53504 S2 * | ca. 300% |
| Density | 1.62 ± 0.05 g/cm ³ |
| Volume change, DIN EN ISO 10563 | ≤ 3 % |
| Temperature resistance after curing | - 40 °C to + 90 °C |
| Application temperature | + 5 °C to + 30 °C |

All measurements were performed under normal conditions (23 $^\circ C$ and 50 % relative humidity).

* The data are based on measurements after 3 months

Application

Tension peaks on assembly parts are avoided by plane bonding. Flexible large surface bonding and sealing in the areas of metal, apparatus and machine construction, plastics technology, airconditioning and ventilation systems, car body, wagon, vehicle and container construction. Installation of sound absorbing elements, large area bonding, bonding of honeycomb panels, sandwich panel etc. Suitable for flexible bonding of teak, larch, doussie, douglas fir, pitch pine, deck covering of plastics (except polyethylene and polypropylene), steel, aluminium and prefabricated deckboards. Suitable for flexible bonding of wood, precious wood, solid flooring, solid wood flooring, exotic parquet, laminate flooring, teak flooring based on PVC, aluminium and stainless steel, sheet metal, cork, linoleum flooring with textile back, bamboo flooring. Avoid contact points to non-system adhesives and sealants of other manufacturers.

Substrate range

Suitable materials are metals, powder-coated, varnished, galvanised, anodised, chromed or hot zinc dipped surfaces, various plastics and ceramics. Teak, larch, doussie, douglas fir, pitch pine, deck covering of plastic (except polyethylen and polypropylen) on boat plywood, fiberglass, aluminium and steel. Note: The substrate must be free of rust and treated against corrosion. Due to the large variety of different plastics and compositions as well as materials which are susceptible to cracks, preliminary tests are recommended.

Meets the standards

- EMICODE EC1Plus
- Eurofins IAC Gold
- IMO FTPC Parts 2+5

Technical data sheet Merbenit DB50

Substrate preparation

The substrate must be tensile- and compression-resistant, sufficient surface solid, free of cracks, clean, flat and dry and free of release agents. Make sure the surface is protected against corrosion and avoid contact points to non-system adhesives and sealants from other manufacturers. The compatibility with adjacent materials, coatings etc. must be determined in advance.

Adhesion promoter

With most materials a good adhesion is achieved even without adhesion promoter. On structurally weak, porous and difficult surfaces we always recommend the use of an appropriate adhesion promoter. Preliminary tests are recommended.

Processing

- Avoid sun and rain influence on the work surface during bonding process
- Apply the adhesive with a notched trowel (toothing approx. 5 x 5 mm) evenly on the ground and insert the installation element within the working time on adhesive bed by thoroughly knocking
- To accelerate the curing or for large scale bonding of two non-breathing substrates a prior spraying with water (10 g/m²) is recommended
- Non-cured adhesive can be removed with rubbing alcohol or isopropyl
- Cured adhesive can only be removed mechanically

Chemical resistance

- Good against water, aliphatic solvents, oils, grease, diluted inorganic acids and alkalis
- Moderate against esters, ketone and aromatics
- Not resistant against concentrated acids and chlorinated hydrocarbons

Colours black

other colours on request

Packaging Buckets of 16 kg on pallet of 33 units

Shelf life and storage conditions

- 12 months from date of production in original packaging
- Store cool and dry (10 25 °C)
- Further information on request

Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

merz+benteli ag

Freiburgstrasse 616 CH - 3172 Niederwangen Phone +41 31 980 48 48 Fax +41 31 980 48 49 info@merz-benteli.ch www.merz-benteli.ch

Last Update: 19.05.2020

Our information is based on experiences in lab and practice. Their publication occurs,however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical characteristics according to the Technical Data Sheets up to their expiry date which is available upon request and which is available on our website. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne

